



Protective & Marine Coatings

MKEC ENGINEERING, INC.
411 North Webb Road - Wichita, KS 67206

- Reviewed Reviewed As Noted
- Revise and Resubmit Rejected
- Not Required by the Contract Documents

Reviewed for conformance with the design concept of the project and compliance with the information given in the contract documents. Contractor is responsible for: dimensions to be confirmed and correlated at the job site; information that pertains solely to the fabrication process or to techniques of construction; and coordination of work of all other trades. If "Resubmit" or "Rejected" are not checked resubmission is neither desired or required.

By: Mark Buckingham Date: 10/24/2016

ACROLON™ 218 HS ACRYLIC POLYURETHANE

B65-600
B65-650
B65V600

GLOSS SERIES
SEMI-GLOSS SERIES
HARDENER

Revised: July 23, 2013

PRODUCT INFORMATION

5.22

PRODUCT DESCRIPTION	RECOMMENDED USES
---------------------	------------------

A Tyler -
a I spoke with the City. The interior piping should be painted purple from the pump discharge flange downstream. The City requested a "true" purple color.
p Mark,
I was told by Sherwin Williams at the special paint that will be used in the wet well has very limited color availability, either white or gray. I planned to use gray in this area and then from the point up into the pump rooms and ending at the pump flange will be the "true" purple. The only exception will be the pre-finished valves that were painted a light blue in the factory, as we did not intend to paint over those.
F Thank you,
c Tyler J. Dehn

Volume Solids: 65% ± 2%, mixed, may vary by color
Weight Solids: 78% ± 2%, mixed, may vary by color
VOC (EPA Method 24): Unreduced: <300 g/L; 2.5 lb/gal
 mixed Reduced 10% with R7K15: <340 g/L; 2.8 lb/gal
 mixed Reduced 9% with MEK, R6K10: <340 g/L; 2.8 lb/gal
Mix Ratio: 6:1 by volume, 1 gallon or 5 gallon mixes premeasured components

Recommended Spreading Rate per coat:		
	Minimum	Maximum
Wet mils (microns)	4.5 (112.5)	9.0 (225)
Dry mils (microns)	3.0 (75)	6.0 (150)
~Coverage sq ft/gal (m²/L)	175 (4.3)	346 (8.5)
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	1040 (25.5)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 6.0 mils wet (150 microns):			
	@ 35°F/1.7°C	@ 77°F/25°C	@ 120°F/49°C
		50% RH	
To touch:	4 hours	30 minutes	20 minutes
To handle:	18 hours	6 hours	4 hours
To recoat:			
minimum:	18 hours	8 hours	6 hours
maximum:	3 months	3 months	3 months
To cure:	14 days	7 days	5 days
Pot Life:	4 hours	2 hours	45 minutes
<i>(reduced 5% with Reducer R7K15)</i>			
Sweat-in-Time:	None		

If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent. Paint temperature must be at least 40°F (4.5°C) minimum.

Shelf Life: Part A* - 36 months, unopened
Part B - 24 months, unopened
Store indoors at 40°F (4.5°C) to 100°F (38°C).
*Aluminum (Part A, Rex # B65SW655) has a shelf life of 24 months.
Flash Point: 55°F (13°C), Seta, mixed
Reducer/Clean Up:
 Spray: Reducer R7K15, MEK R6K10, or R7K111
 Brush / Roll: Reducer #132, R7K132 or R7K111

- Suitable for use in the Mining & Minerals Industry

PERFORMANCE CHARACTERISTICS

Substrate*: Steel
Surface Preparation*: SSPC-SP10/NACE 2
System Tested*:
 1 ct. Macropoxy 646 @ 6.0 mils (150 microns) dft
 1 ct. Acrolon 218 HS Gloss @ 4.0 mils (100 microns) dft
 *unless otherwise noted below

Test Name	Test Method	Results
Abrasion Resistance¹	ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load	43 mg loss
Adhesion	ASTM D4541	975 psi
Corrosion Weathering²	ASTM D5894, 9 cycles, 3024 hours	Rating 10 per ASTM D610, for rusting; Rating 10 per ASTM D714, for blistering
Direct Impact Resistance¹	ASTM D2794	50 in. lb.
Dry Heat Resistance¹	ASTM D2485, Method A	200°F (93°C)
Flexibility¹	ASTM D522, 180° bend, 1/8" mandrel	Passes
Humidity Resistance²	ASTM D4585, 100°F (38°C), 1500 hours	Rating 10 per ASTM D610, for rusting; Rating 10 per ASTM D714, for blistering
Pencil Hardness	ASTM D3363	3H
Salt Fog Resistance²	ASTM B117, 7000 hours	Rating 10 per ASTM D610, for rusting; Rating 9 per ASTM D714, for blistering

Meets the requirements of SSPC Paint No. 36, Level 3 for white and light colors. Dark colors may require a clear coat.
 Complies with ISO 12944-5 C5I and C5M requirements.

Footnotes:
¹ Finish coat only tested
² Primer Zinc-Clad II Plus
 Intermediate Macropoxy 646
 Finish Acrolon 218 HS



Protective & Marine Coatings

ACROLON™ 218 HS ACRYLIC POLYURETHANE

PART A	B65-600	GLOSS SERIES
PART A	B65-650	SEMI-GLOSS SERIES
PART B	B65V600	HARDENER

PRODUCT INFORMATION

5.22

RECOMMENDED SYSTEMS			
	Dry Film Thickness / ct.		
	Mils	(Microns)	
Steel:			
1 ct. Macropoxy 646	5.0-10.0	(125-250)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Steel:			
1 ct. Zinc Clad II Plus	3.0-5.0	(75-125)	
1 ct. Macropoxy 646	5.0-10.0	(125-250)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Steel:			
1 ct. Zinc Clad IV	3.0-5.0	(75-125)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Steel:			
1 ct. Corothane I-GalvaPac Zinc Primer	3.0-4.0	(75-100)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Steel:			
1 ct. Epoxy Mastic Aluminum II	6.0	(150)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Steel:			
1 ct. Recoatable Epoxy Primer	4.0-6.0	(100-150)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Concrete/Masonry:			
1 ct. Kem Cati-Coat HS Epoxy Filler/Sealer	10.0-20.0	(250-500)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
Aluminum/Galvanizing:			
1 ct. DTM Wash Primer	0.7-1.3	(18-32)	
1-2 cts. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
ISO 12944 C5M System:			
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)	
1 ct. Tower Guard Epoxy	5.0-11.5	(125-287.5)	
1 ct. Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)	
FIRETEX ONLY:			
Finish Coat for FIRETEX Hydrocarbon Systems:			
1 ct. Acrolon 218 HS Polyurethane*			

*Consult FIRETEX PFP Specialist for recommended dft range

The systems listed above are representative of the product's use, other systems may be appropriate.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

SURFACE PREPARATION				
Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.				
Refer to product Application Bulletin for detailed surface preparation information.				
Minimum recommended surface preparation:				
* Iron & Steel:	SSPC-SP6/NACE 3, 1-2 mil (25-50 micron) profile			
* Galvanizing:	SSPC-SP1			
* Concrete & Masonry:	SSPC-SP13/NACE 6, or ICRI No. 310.2, CSP 1-3			
* Primer required				
Surface Preparation Standards				
Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusty	D St 2	D St 2	SP 2	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	Pitted & Rusty	D St 3	SP 3	-

TINTING	
Tint Part A with Maxitoner Colorants.	
<ul style="list-style-type: none"> • Extra white tints at 100% tint strength • Ultradeep base tints at 150% tint strength 	
Five minutes minimum mixing on a mechanical shaker is required for complete mixing of color.	

APPLICATION CONDITIONS	
Temperature:	35°F (1.7°C) minimum, 120°F (49°C) maximum (air and surface) 40°F (4.5°C) minimum, 120°F (49°C) maximum (material) At least 5°F (2.8°C) above dew point
Relative humidity:	85% maximum
Refer to product Application Bulletin for detailed application information.	

ORDERING INFORMATION		
Packaging:	1 gallon (3.78L) mix; 5 gallon (18.9L) mix:	
Part A:	.86 gal (3.25L)	4.29 gal (16.2L)
Part B:	.14 gal (0.53L)	0.71 gal (2.7L)
(premeasured components)		
Weight:	11.2 ± 0.2 lb/gal ; 1.3 Kg/L mixed, may vary with color	

SAFETY PRECAUTIONS	
Refer to the MSDS sheet before use.	
Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.	

WARRANTY	
The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.	



Protective & Marine Coatings

ACROLON™ 218 HS ACRYLIC POLYURETHANE

PART A	B65-600	GLOSS SERIES
PART A	B65-650	SEMI-GLOSS SERIES
PART B	B65V600	HARDENER

Revised: July 23, 2013

APPLICATION BULLETIN

5.22

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Iron & Steel

Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Commercial Blast Cleaning per SSPC-SP6/NACE 3. For better performance, use Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (1-2 mils / 25-50 microns). Prime any bare steel the same day as it is cleaned or before flash rusting occurs.

Aluminum

Remove all oil, grease, dirt, oxide and other foreign material by Solvent Cleaning per SSPC-SP1. Primer required.

Galvanized Steel

Allow to weather a minimum of six months prior to coating. Solvent Clean per SSPC-SP1. When weathering is not possible, or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP7 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned or before flash rusting occurs. Primer required.

Concrete and Masonry

For surface preparation, refer to SSPC-SP13/NACE 6, or ICR1 No. 310.2, CSP 1-3. Surfaces should be thoroughly clean and dry. Concrete and mortar must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, dirt, form release agents, moisture curing membranes, loose cement and hardeners. Fill bug holes, air pockets and other voids with Steel-Seam FT910. Primer required.

Follow the standard methods listed below when applicable:

ASTM D4258 Standard Practice for Cleaning Concrete.
ASTM D4259 Standard Practice for Abrading Concrete.
ASTM D4260 Standard Practice for Etching Concrete.
ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete.
SSPC-SP 13/Nace 6 Surface Preparation of Concrete.
ICRI No. 310.2 Concrete Surface Preparation.

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Power Tool Cleaning	C St 3	C St 3	SP 3	-
Pitted & Rusted	D St 3	D St 3	SP 3	-

APPLICATION CONDITIONS

Temperature:	35°F (1.7°C) minimum, 120°F (49°C) maximum (air and surface) 40°F (4.5°C) minimum, 120°F (49°C) maximum (material) At least 5°F (2.8°C) above dew point
Relative humidity:	85% maximum

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reducer/Clean Up:

Spray.....	Reducer R7K15, MEK R6K10, or R7K111
Brush/Roll	Reducer #132, R7K132, or R7K111
If reducer is used, reduce at time of catalyzation.	

Airless Spray

Pressure.....	2500 - 2800 psi
Hose.....	3/8" ID
Tip013" - .017"
Filter	60 mesh
Reduction.....	As needed up to 10% by volume with R7K15 or R7K111, or up to 9% with MEK, R6K10*

Conventional Spray

Gun	Binks 95
Cap	63P
Atomization Pressure.....	50 - 70 psi
Fluid Pressure.....	20 - 25 psi
Reduction.....	As needed up to 10% by volume with R7K15 or R7K111, or up to 9% with MEK, R6K10*

Brush

Brush.....	Natural Bristle
Reduction.....	As needed up to 10% by volume*

Roller

Cover	3/8" woven with solvent resistant core
Reduction.....	As needed up to 10% by volume*

If specific application equipment is not listed above, equivalent equipment may be substituted.

* Note: Reducing more than maximum recommended level will result in VOC exceeding 340g/L



Protective & Marine Coatings

ACROLON™ 218 HS ACRYLIC POLYURETHANE

PART A	B65-600	GLOSS SERIES
PART A	B65-650	SEMI-GLOSS SERIES
PART B	B65V600	HARDENER

APPLICATION BULLETIN

5.22

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mix contents of each component thoroughly with low speed power agitation. Make certain no pigment remains on the bottom of the can. Then combine six parts by volume of Part A with one part by volume of Part B (premeasured components). Thoroughly agitate the mixture with power agitation. Re-stir before using.

If reducer is used, add only after both components have been thoroughly mixed.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	4.5 (112.5)	9.0 (225)
Dry mils (microns)	3.0 (75)	6.0 (150)
~Coverage sq ft/gal (m ² /L)	175 (4.3)	346 (8.5)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1040 (25.5)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 6.0 mils wet (150 microns):

	@ 35°F/1.7°C	@ 77°F/25°C 50% RH	@ 120°F/49°C
To touch:	4 hours	30 minutes	20 minutes
To handle:	18 hours	6 hours	4 hours
To recoat:			
minimum:	18 hours	8 hours	6 hours
maximum:	3 months	3 months	3 months
To cure:	14 days	7 days	5 days
Pot Life:	4 hours	2 hours	45 minutes
<i>(reduced 5% with Reducer R7K15)</i>			
Sweat-in-Time:	None		

If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent. Paint temperature must be at least 40°F (4.5°C) minimum.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with Reducer #132, R7K132. Clean tools immediately after use with Reducer #132, R7K132. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, and adhesion.

Do not apply the material beyond recommended pot life.

Do not mix previously catalyzed material with new.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with Reducer #15, R7K15 or MEK, R6K10.

Mixed coating is sensitive to water. Use water traps in all air lines. Moisture contact can reduce pot life and affect gloss and color.

Quick-Thane Urethane Accelerator is acceptable for use. See data page 5.97 for details.

E-Z Roll Urethane Defoamer is acceptable for use. See data page 5.99 for details.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.